

COMPOSITE HOSES





TAILORED SOLUTIONS+



WHY PLASCORP?

For 60+ years we've manufactured and supplied composite hoses, ducting, PVC pipes plus mine ventilation and steel reinforcing to various industries in Australia. But our biggest plus, is our ability to customise and tailor solutions to solve our customers' challenges.

OUR RANGE

Petrol Hose Range	4-6
Standard	4
Heavy Duty	5
Lightweight	5
Aviation	5
Vapour Recovery	6
Hot Bitumen	6
Chemical Hose Range	7-9
Standard	7
SSW	8
CS	8
ASS	9
PTSS	9
Incorrect and Correct Usage	9
Composite Hose Assembly Testing	10
Pressure Loss Chart	10

Plascorp is one of Australia's leading privately owned manufacturing and distribution companies. We have invested significantly in quality European equipment to maximise manufacturing efficiency and enable value-add products to be produced for customers, expanding our operations in Melbourne, Sydney, Brisbane and Perth.

The company draws from years of experience in the aviation, petrochemical, construction, civil infrastructure and mining industries to produce custom or 'made to order' designs and product solutions that best meet our customer's specification requirements. Our superior service support includes working closely with our customers from planning stage through to a project's completion. We have a network of dedicated and client-focused sales teams and branches across all major cities.

PRODUCTS YOU CAN TRUST

All our products are manufactured to the relevant Australian Standards and tested under strict quality control procedures. We hold numerous standards licences. Plascorp manufacturing is approved and certified in accordance with ISO 9001.

We have been manufacturing thermoplastic composite hoses for over 50 years. Our composite hose range is predominately used with suction and delivery of petroleumbased products, chemicals, acids and alkalis. Applications include chemical process plants, transport tankers, refineries and other industrial applications. Products are available through an extensive distribution network.

Local manufacturing enables us to have control over our production capabilities ensuring a consistent product to meet our clients' needs. It also provides the flexibility to customise products and to ensure we can meet the most challenging deadlines for each project.







SHORTER LEAD TIMES







TAILOR MADE COMPOSITE HOSES

When it comes to composite hoses, understanding the chemistry of the proposed use is important to ensure the correct materials are used for performance and longevity.

COMPOSITE HOSE BENEFITS

Plascorp composite hoses consist of various layers encapsulated between internal and external spiral wire helives

The application and pressure rating of the hose dictates the composition, number of layers and the type of wire. The unique wire helixes deliver the pressure handling characteristics and a tough PVC coated fabric forms the outer cover.

Our composite hose construction results in a light and flexible hose with a relatively short bend radius which is suitable for a wide variety of uses.

KEY BENEFITS INCLUDE:

- Customised end fittings
- Customise construction to chemistry requirements
- Wire helix construction adds strength and durability
- Efficient and economical
- Durable high-strength outer material
- Good puncture and abrasion resistance





PETROL HOSE RANGE AS 2683-2000

Our Petrol Hose AS 2683-2000 range is designed and manufactured specifically for the demands of the petro-chemical industry. The polypropylene film and fabric construction handles hydrocarbon-based products. The internal and external wire helix wires deliver the pressure handling characteristics and a tough PVC-coated fabric forms the outer cover.

Description	Code	Туре	Conforming	Grade	Elec		٨	1ax Work	ing Pres	sure (kPa	ı @ Ambi	ent Temp	o)	
			Standard		Kind	3/4	1	11/4	11/2	2	21/2	3	4	6
Petrol Hose STD Green with reflective yellow stripe	1000	1	AS 2683-2000	3	1	*	700	700	700	700	700	700	700	700
Petrol Hose HD Black with no stripe	901	1	AS 2683-2000	3	1	-	1400	1400	1400	1400	1000	1000	1000	1000
Petrol Hose LW Yellow with reflective green stripe	1003	1	AS 2683-2000	3	1	-	-	-	-	600	500	500	400	*
Aviation Hose Black with green stripe	AVA	1	AS 2683-2000	3	1	*	*	*	700	700	*	700	700	*
Vapour Recovery Hose Black with yellow stripe	VRH	1	AS 2683-2000	3	1	-	-	-	-	*	*	*	400	*
Hot Bitumen White with no stripe	966	2	AS 2475	2	1	700	700	700	700	600	500	500	-	-

Type 1 hose is designed for suction and discharge and to be non-collapsible.

Type 2 hose is designed for discharge only and to be non-collapsible.

Grade refers to the hose suitability to handle aromatic hydrocarbon content.

Grade 1 hose is suitable for fuels containing up to 30% aromatic hydrocarbon content.

Grade 2 hose is suitable for fuels containing up to 50% aromatic hydrocarbon content. Grade 3 hose is suitable for fuels containing over 50% aromatic hydrocarbon content. Kind 1 hose has an electrical resistance not greater than 1.0 ohm/m

PETROL COMPOSITE HOSE STANDARD / Type 1 / Grade 3 / Kind 1 - CODE 1000



Colour: Green with yellow stripe
Temperature Range: -30°C to +80°C
Internal wire: Galvanised steel

Applications: Lightweight, flexible hose designed for suction and delivery of petroleum-based products. Suitable for road and rail tankers.

NOM (inches)	ID (mm)	OD (mm)	Min. Bend Radius (mm)	Working Pressure kPa at 20°C	Weight (kg/m)	Coil Length (m)
1	25	32	60	700	0.8	20
1 1/4	32	38	75	700	1	20
1 1/2	39	48	75	700	1.3	20
2	51	63	90	700	1.6	20
21/2	63	75	100	700	2.4	20
3	76	90	125	700	2.8	20
4	102	112	200	700	4.1	20
6	152	170	400	700	7.8	to order

 $^{^{\}ast}$ Hoses and test pressures are available on request.

PETROL COMPOSITE HOSE HEAVY DUTY / Type 1 / Grade 3 / Kind 1 - CODE 901



AS 2683-2000

Temperature Range: -30°C to +80°C Internal wire: Galvanised steel Applications: Used for ship to shore and general-purpose heavy-duty applications conveying petroleum products. Suitable for heavy-duty discharge for road and rail tankers docks, thin to show

NOM (inches)	ID (mm)	OD (mm)	Min. Bend Radius (mm)	Working Pressure kPa at 20°C	Weight (kg/m)	Coil Length (m)
1	25	35	100	1400	0.9	20
1 1/4	32	42	125	1400	1.3	20
1 1/2	39	50	140	1400	1.5	20
2	51	65	170	1400	1.9	20
2 1/2	63	76	200	1000	3	20
3	76	90	270	1000	3.4	20
4	102	120	340	1000	6.5	20
6	152	180	700	1000	12.4	to order

PETROL COMPOSITE HOSE LIGHTWEIGHT / Type 1 / Grade 3 / Kind 1 - CODE 1003



AS 2683-2000

Colour: Yellow with green stripe Temperature Range: -30°C to +80°C

Internal wire: Aluminium External wire: Galvanised stee Applications: Super-lightweight hose for suctions and delivery of petroleum-based products where ease of handling is paramount

NOM (inches)	ID (mm)	OD (mm)	Min. Bend Radius (mm)	Working Pressure kPa at 20°C	Weight (kg/m)	Coil Length (m)
2	51	63	90	600	1.25	20
2 1/2	63	75	100	500	1.75	20
3	76	90	125	500	2	20
4	102	112	200	400	2.5	20

AVIATION HOSE / Type 1 / Grade 3 / Kind 1 - CODE AVA



AS 2683-2000

Temperature Range: -30°C to +80°C

Internal wire: Stainless steel External wire: Galvanised steel Applications: Specially designed for the suction

NOM (inches)	ID (mm)	OD (mm)	Min. Bend Radius (mm)	Working Pressure kPa at 20°C	Weight (kg/m)	Coil Length (m)
1 1/2	39	48	75	700	1.3	20
2	51	63	90	600	1.6	20
3	76	90	125	500	2.8	20
4	102	112	200	400	4.1	20

VAPOUR RECOVERY HOSE / Type 1 / Grade 3 / Kind 1 - CODE VRH



AS 2683-2000

Colour: Black with yellow stripe
Temperature Range: -30°C to +80°C

External wire: Galvanised steel

Applications: Suitable for the collection or transfer of hydrocarbon vapours within the petroleum industry.

NOM (inches)	ID (mm)	OD (mm)	Min. Bend Radius (mm)	Working Pressure kPa at 20°C	Weight (kg/m)	Coil Length (m)
4	102	112	200	400	4.1	20
4	102	112	200	400	4.1	30

HOT BITUMEN HOSE / Type 2 / Grade 2 / Kind 1 - CODE 966



AS 2475-1001

Colour: White

Temperature Range: -30°C to +180°C Internal wire: Galvanised steel

External wire: Stainless steel

Applications: Made from polyester film and fabric designed for high-temperature operation, this hose is ideal for the transfer of hot bitumen via gravity, suction or pressure. This hose is suitable for use with bitumen up to 180°C. It is ideally suited for road tanker loading and discharge, in plant transfer, spraying and spray bar applications. This hose is also suitable for conveying high aromatic content fuels.

NOM (inches)	ID (mm)	OD (mm)	Min. Bend Radius (mm)	Working Pressure kPa at 20°C	Weight (kg/m)	Coil Length (m)
3/4	19	28	125	700	0.8	20
1	25	35	125	700	0.9	20
1 1/4	32	43	130	700	1	20
1 1/2	39	50	150	700	1.5	20
2	51	68	200	600	2	20
2 1/2	63	78	250	500	2.8	20
3	76	90	280	500	3.5	20
4	102	112	200	400	4.1	20



Note: This hose is not recommended for use close to direct external radiant heat as the cover is not flame-retardant. Hoses should be flushed with diesel or kerosene after use. Cleaning with steam or direct external heat is not recommended.

CHEMICAL HOSE RANGE AS 2594-1983

Our Chemical Hose AS 2594-1983 range is suitable for the suction and delivery of a wide range of chemicals. Constructed of polypropylene films and fabrics, the hoses are resistant to most acids, alkalis and solvents. Internal and external helix wires bind the hose together and deliver superior pressure handling. A tough PVC-coated fabric cover forms the outer cover for durability.

Depending on chemical resistance requirements and the material being conveyed, different internal and external wire combinations are available. Please consult with us for compatibility.

Description	Code	Туре	Conforming		M	lax Worki	ng Pressu	re (kPa @	Ambient	Temp) in	:h	
			Standard	3/4	1	11/4	11/2	2	2 1/2	3	4	6
Chemical Hose STD Grey with red stripe	951	1	AS 2594-1983	*	1400	1400	1400	1200	1000	1000	1000	-
Chemical Hose SSW Grey with blue stripe	952	1	AS 2594-1983	*	1400	1400	1400	1200	1000	1000	1000	-
Chemical Hose CS Orange	969	1	AS 2594-1983	*	1400	1400	1400	1200	1000	1000	1000	1000
Chemical Hose ASS Orange with blue stripe	ASS	1	AS 2594-1983	*	1400	1400	1400	1200	1000	1000	1000	1000
Chemical Hose PTSS Red with white stripe	2200	1	AS 2594-1983	-	*	-	*	1200	*	1000	1000	*

Type I hose is designed for suction and discharge and to be non-collapsible.

CHEMICAL COMPOSITE HOSE STANDARD / Type 1 - CODE 951



AS 2594-1983

Colour: Grey with red stripe

Temperature Range: -30°C to +100°C Internal wire: PP-coated galvanised steel

External wire: Galvanised stee

NOM (inches)	ID (mm)	OD (mm)	Min. Bend Radius (mm)	Working Pressure kPa at 20°C	Weight (kg/m)	Coil Length (m)
1	25	38	100	1400	0.9	20
1 1/4	32	45	125	1400	1.3	20
1 1/2	39	50	140	1400	1.5	20
2	51	65	170	1200	1.8	20
2 1/2	63	78	200	1000	2.7	20
3	76	92	270	1000	3.3	20
4	102	120	340	1000	6.3	20

^{*} Hoses and test pressures are available on request.

CHEMICAL COMPOSITE HOSE SSW / Type 1 - CODE 952



ΔS 2594-1983

Colour: Grey with blue stripe

Temperature Range: - 30°C to +100°C nternal wire: PP coated galvanised steel

External wire: Stainless steel

NOM (inches)	ID (mm)	OD (mm)	Min. Bend Radius (mm)	Working Pressure kPa at 20°C	Weight (kg/m)	Coil Length (m)
1	25	38	100	1400	0.9	20
1 1/4	32	45	125	1400	1.3	20
1 1/2	39	50	140	1400	1.5	20
2	51	65	170	1200	1.8	20
2 1/2	63	78	200	1000	2.7	20
3	76	92	270	1000	3.3	20
4	102	120	340	1000	6.3	20

CHEMICAL COMPOSITE HOSE CS / Type 1 - CODE 969



AS 2594-1983

Temperature Range: - 30°C to +100°C

Internal wire: Stainless steel External wire: Galvanised steel


NOM (inches)	ID (mm)	OD (mm)	Min. Bend Radius (mm)	Working Pressure kPa at 20°C	Weight (kg/m)	Coil Length (m)
1	25	38	100	1400	0.9	20
1 1/4	32	45	125	1400	1.3	20
1 1/2	39	50	140	1400	1.5	20
2	51	65	170	1200	1.8	20
2 1/2	63	78	200	1000	2.7	20
3	76	92	270	1000	3.3	20
4	102	120	340	1000	6.3	20
6	152	180	700	1000	12.4	to order

ROPE LAGGING

All hoses can be supplied with polypropylene rope lagging. It is necessary to specify at time of ordering. Lagging insulates and protects the hose from abrasion but doubles the bend radius of the hose.

NOM (inches)	NOM Diameter (mm)	Rope Diameter (mm)
1	25	8
11/4	32	8
11/2	39	8
2	51	8
2 1/2	63	10
3	76	10
4	102	10
6	152	12

CHEMICAL COMPOSITE HOSE / Type 1 - CODE ASS



AS 2594-1983

Colour: Orange with Blue Stripe

Temperature Range: - 30°C to +100°C

nternal wire: Stainless steel External wire: Stainless steel

NOM (inches)	ID (mm)	OD (mm)	Min. Bend Radius (mm)	Working Pressure kPa at 20°C	Weight (kg/m)	Coil Length (m)
1	25	38	100	1400	0.9	20
1 1/2	39	50	140	1400	1.5	20
2	51	65	170	1200	1.8	20
2 1/2	63	78	200	1000	2.7	20
3	76	92	270	1000	3.3	20
4	100	120	340	1000	6.3	20
6	152	180	700	1000	12.4	to order

CHEMICAL COMPOSITE HOSE PTSS / Type 1 - CODE 2200



AS 2594-1983

Colour: Red with white stripe

Temperature Range: - 30°C to +100°C

Internal wire: Stainless steel

External wire: Stainless steel

Applications: PTFE lined for increased resistance to aggressive chemicals.

Heavy duty (Code 2201) and lightweigh (Code 2203) available upon request.

NOM (inches)	ID (mm)	OD (mm)	Min. Bend Radius (mm)	Working Pressure kPa at 20°C	Weight (kg/m)	Coil Length (m)
2	51	65	175	1400	1.85	20
3	76	92	300	1400	4.15	20
4	102	120	350	1400	4.8	20

INCORRECT AND CORRECT USAGE
























COMPOSITE HOSE ASSEMBLY TESTING

All hose assemblies are hydrostatically pressure and electrically tested in accordance with standards AS2683/AS2594 and AS1180

It is recommended that composite hose assemblies be hydrostatically tested at least once every 12 months and electrically tested every 6 months in accordance with the appropriate standards for the hose.


For hose assemblies where there is a difference in pressure rating between hose and end couplings, the maximum working pressure of the assembly will be based on the lowest rated component. For instance, if the hose has a pressure rating of 1000kPa and the end couplings have a pressure rating of 700kPa, the maximum working pressure of hose assembly will be 700kPa. This assembly will be hydrostatically tested in accordance with the relevant standards with a max working pressure of 700kPa.

All assemblies will have a hose tag attached for proof of testing.


WIRE WHIPPED CRIMPED TEST TAG







PRESSURE LOSS FLOW CHART



For open end flow

- Maximum obtainable
 Petrol Codes 1000 and 1003
- Maximum on Petrol Code 901 and Chemical Codes 951/952/969

- + PVC PIPES
- + STEEL REO
- **+ COMPOSITE HOSES**
- + VENTILATION
- + DUCTING


For 6O+ years we've manufactured and supplied PVC pipes plus composite hoses, steel reo, ventilation and ducting to various industries in Australia. But our biggest plus, is our ability to customise and tailor solutions to solve our customers' challenges.


- Range of sizes and custom colours and lengths available
- Fabricating steel to tight tolerances
- Custom slotting and threading
- Ability to fully customise to meet needs













For 60+ years we've manufactured and supplied PVC pipes plus composite hoses, ventilation and ducting to various industries. But our biggest plus, is our ability to customise and tailor solutions to solve our customers' challenges.

We started manufacturing PVC Pipes and flexible ducting in the late 1950's. Our current head office and manufacturing centre in Melbourne, commenced operations in 1961 and has since grown to over three hectares. It accommodates our ever-evolving manufacturing and product tailoring capabilities.

In addition to our Australian customer base, we now supply a range of products in New Zealand, South East Asia, South Africa and the Middle East.

Our parent company, Geofabrics has branches throughout Australia, New Zealand, Papua New Guinea and the Pacific so can deliver product where you need it, when you need it, while providing local expertise to support your project.



45 Chambers Rd ALTONA NORTH VIC 3025



35a Berger St SOUTH WINDSOR NSW 2756



103 Bancroft Rd PINKENBA QLD 4008



32 Clune St BASSENDEAN WA 6054



19 Druces Rd WIRI AUCKLAND NZ 2104

Visit plascorp.com.au or call 1300 30 13 13

IMPORTANT NOTICE - DISCLAIMER - The information contained in this brochure is general in nature. In particular the content of this brochure does not take account of specific conditions that may be present at your site. For full disclaimer and further information regarding installation visit plascorp.com.au/disclaimer © Copyright held by Plascorp Pty Ltd. All rights are reserved and no part of this publication may be copied without prior permission. Published September 2024.



